

Cement-lime Based Render

Guide Formulation

Mineral base mixture	Parts by Weight
Portland cement	10-15
Hydrated lime	3-5
Limestone flour < 0,1 mm	12-18
Limestone or quartz sand 0,1 - 1,5 mm	60-70
Perlite 0- 1 mm	0-0.5

Additives	Parts by Weight
KimaCell Cellulose ether	0.08-0.13
Starch ether	0.01-0.03
Air entraining, wetting and plasticizing agent	0.01-0.03
Hydrophobing agent (stearate/oleate)	0.1-0.2