

Gypsum based joint filler

Guide Formulation

Mineral base mixture	Parts by Weight
Gypsum hemihydrate < 0,1 mm	60-90
Limestone flour < 0,1 mm	10-40

Additives	Parts by Weight
KimaCell Cellulose ether	0.4-0.6
Setting retarder	0.03-0.2

Optimizing additives	Parts by Weight
PVA 2488	0.5-1.5
Cellulose fibres < 0,4 mm	0.2-0.5
Redispersible Polymer powder	1-2