

Self Leveling Floor Compound

Guide Formulation

Mineral base mixture	Parts by Weight
Portland cement	35-45
High aluminate cement	2 -5
Limestone flour < 0,1 mm	5-10
Quartz sand 0,1 - 0,4 mm	38 -42

Additives	Parts by Weight
KimaCell Cellulose ether	0,05-0,15
Redispersible Polymer powder	1-2
Superplasticizer	0,2- 0,7
Powder defoamer	0,15-0,2

Optimizing additives	Parts by Weight
Hydrated lime	1-2
Setting retarder	0,1-0,3